

SAV 3yr

Features

- 95um monomeric vinyl, 168gsm 2-side PE coated liner and solvent acrylic adhesive;
- Available with grey air-free removable and permanent adhesive, and clear removable and permanent adhesive;
- Suitable for everyday short-term signage and P.O.S applications on flat surfaces;
- Outdoor durability* for up to 3 years;
- Dimensionally stable for easy converting;
- Wide range of temperature adaptability;
- Versatile adhesive suitable for most substrates and removable with heat and/or chemicals;
- Air channel technology for easy installation;
- Printable with latex, UV, eco-solvent and solvent wide format ink systems.

Product Details

.Roll size	1.37m x 50m as standard (other sizes available ex production)
Expected durability*	Up to 3 years, unprinted on vertical exterior surfaces.
Printability	Latex, UV, solvent & eco-solvent inkjet.
Removability	Easy to be removed for up to 12 months from installation when installed following correct protocols.
Shelf Life	2 years stored at 23°C and 50% relative humidity.

Graphic application - recommendations		
Surface	Dust free, oil free, smooth, flat, surfaces	
Temperature	2°C - 50°C air and substrate	
Application method	Dry	

Masterjet SAV 3yr Page **1** of **5**

Technical Characteristics

Masterjet SAV 3yr - Gloss White, <u>Grey Removable</u> Adhesive, <u>Air Release</u> Liner

Characteristic	Property
FILM:	
Type/Colour/Finish	PVC/White/Gloss
Film thickness (without adhesive)	• 95 µ ± 10% (without liner and adhesive)
Elongation	• ≥50%
Tensile Strength	• ≥20Mpa
Dimensional Stability	• 0.5mm max
ADHESIVE:	
• Type	Solvent based pressure-sensitive acrylic, removable
Colour	Grey
Thickness	20±2 micron
Initial Tack	• ≥6N/m
Holding Power	• ≥8N/m
Release Force	• 50-150g/50mm
Service Temperature	• -15°C to +60°C
	•
LINER:	
• Type	2-side PE coated kraft with air channel technology
Colour	White
Weight	• 165gsm ± 10%

Masterjet SAV 3yr Page **2** of **5**

Technical Characteristics cont.

Masterjet SAV 3yr - Gloss White, <u>Grey Permanent</u> Adhesive, <u>Air Release</u> Liner

Characteristic	Property
FILM:	
Type/Colour/Finish	PVC/White/Gloss
Film thickness (without adhesive)	• 95 μ ± 10% (without liner and adhesive)
Elongation	• ≥50%
Tensile Strength	• ≥20Mpa
Dimensional Stability	• 0.5mm max
ADHESIVE:	
• Type	Solvent based pressure-sensitive acrylic, permanent
• Colour	• Grey
Thickness	20±2 micron
Initial Tack	• ≥8N/m
Holding Power	• ≥10N/m
Release Force	• 50-150g/50mm
Service Temperature	• -15°C to +60°C
LINER:	
• Type	2-side PE coated kraft with air channel technology
Colour	White
Weight	• 165gsm ± 10%

Masterjet SAV 3yr Page **3** of **5**

Technical Characteristics cont.

Masterjet SAV 3yr - Gloss White, <u>Clear Removable</u> Adhesive

Characteristic	Property
FILM:	
Type/Colour/Finish	PVC/White/Gloss
Film thickness (without adhesive)	 95 μ ± 10% (without liner and adhesive)
Elongation	• ≥50%
Tensile Strength	• ≥20Mpa
Dimensional Stability	• 0.5mm max
Flammability	Self-extinguishing
ADHESIVE:	
Type	Solvent based pressure-sensitive acrylic, removable
Colour	Clear
Thickness	20±2 micron
Initial Tack	• ≥6N/m
Holding Power	• ≥8N/m
Release Force	• 50-150g/50mm
Service Temperature	• -15°C to +60°C
LINER:	
Type	2-side PE coated kraft
Colour	• White
Weight	• 165gsm ± 10%

Masterjet SAV 3yr Page 4 of 5

Technical Characteristics cont.

Masterjet SAV 3yr - Gloss White, <u>Clear Permanent</u> Adhesive

Characteristic	Property
FILM:	
Type/Colour/Finish	PVC/White/Gloss
Film thickness (without adhesive)	95 μ ± 10% (without liner and adhesive)
Elongation	• ≥50%
Tensile Strength	• ≥20Mpa
Dimensional Stability	• 0.5mm max
Flammability	Self-extinguishing
ADHESIVE:	
Type	Solvent based pressure-sensitive acrylic, permanent
Colour	Clear
Thickness	20±2 micron
Initial Tack	• ≥8N/m
Holding Power	• ≥10N/m
Release Force	• 50-150g/50mm
Service Temperature	• -15°C to +60°C
LINER:	
Type	2-side PE coated kraft
Colour	White
Weight	• 165gsm ± 10%

Masterjet SAV 3yr Page **5** of **5**June 2019