



permanent



high tack



60 mic



## decal cutting vinyl P HT 60

Cutting vinyl, with 60 mic polymeric PVC film, high performance high tack permanent adhesive and 125 gr. Clay coated kraft paper liner.

### SUBSTRATE

- PVC soft calendered, made from polymeric resins.

Finish	<b>Glossy:</b> Black, White, Cherry Red, Royal Blue, Sunflower Yellow, Green, Dark Grey		
	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	60	± 10%	ASTM D 1593
Weight (g/m <sup>2</sup> )	82	± 10%	ASTM D 1593
Gloss (60°C) (%)	≥ 65		ASTM D 523

### ADHESIVE

- Clear acrylic based, permanent high tack

	<i>Value</i>	<i>Standard</i>
Peel Adhesion steel 20 min (N/25mm)	> 13	FINAT FTM1
Peel Adhesion steel 24 h (N/25mm)	> 20	FINAT FTM1
Shrinkage (mm)	0,2	FINAT FTM 14
Application temperature (°C)	> 10	
Service temperature (°C)	-10 a 70	

### LINER

- Clay coated kraft paper

	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	118	± 10%	ISO 534
Weight (g/m <sup>2</sup> )	125	± 10%	ISO 536

## decal cutting vinyl P HT 60

### DURABILITY

- INDOOR: < 5 years / OUTDOOR: < 3 years
- Shelf Life: 24 months from the date of manufacture, applicable only to material that has not been processed, and stored according to the following conditions:
  - This material must be stored at a temperature of  $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$  and  $50\% \pm 5\%$  relative humidity, without major climate deviations.
  - The storage area must be dry and clean.
  - Keep the material in the original package when not in use, in order to protect it from dust and contamination.
  - Do not expose to direct sunlight or heat sources.
  - The product must be stored vertically, so that its quality is not compromised.

---

### APPLICATIONS

- Application surface: flat, curve (convex)
- Substrate not recommended for floor graphics (areas with car traffic); flexible or low energy substrates; non-flat surfaces; carton walls painted or unpainted; plaster walls; wallpaper; unclean or rough surfaces; surfaces with degraded paint.
- Do not expose to combustible vapors or spills.
- Surfaces on which the material will be applied must be carefully cleaned and free of dust, grease or any other contamination that may affect the material adhesion.
- Non-vertical application results in a significant reduction in durability, as well as climate and angles of sun exposure. It is recommended that the film remains at least 24 hours at the temperature of the workplace before it is used.
- There may be other factors not described here that may influence the performance in the use.

---

### IMPORTANT REMARKS

- Decal is not responsible for the ease or speed of removal of the applied material. It is necessary to have into account the appropriate air and substrate temperatures.
- The user must determine the material's compatibility with the intended specific application, before using it.
- The data provided in this information is based on our knowledge and experience. It is intended to be a source of information and is not a guarantee. It can be subject to change without previous notice.
- Decal is not responsible for misuse or improper storage, never being responsible for loss or damage to third parties.

Revision date of the technical data sheet: 11.07.22  
Approved by: SC

Please, check our website [www.decal-adhesive.com](http://www.decal-adhesive.com) for additional information or request any clarification needed from our technicians.